

UNO - HM - 910

UNOFIX HM 910 - Melamine Edge Pre-gluing Hotmelt

A medium-viscosity hotmelt for pre-gluing melamine surfaces, providing even roller application, fast drying and reliable performance on high-speed machines.



DESCRIPTION

UNOFIX HM 910 is a hotmelt adhesive for pre-gluing melamine surfaces before edge application. Its medium viscosity delivers an even spread through roller application at the appropriate operating conditions.

It supports fast drying on high-speed machines and maintains reliable performance across different melamine surfaces. The resulting film combines elasticity with hardness for dependable processing and bonding performance.

UNOFIX HM 910 runs on all roller-type melamine back-coating machines. It is user-friendly, helps limit carbonisation in the adhesive melting tank and can reduce consumption compared with equivalent products.

KEY BENEFITS

- ✓ Consistent pre-gluing of melamine surfaces
- ✓ Clean, even application at suitable operating conditions
- ✓ Reliable processing batch after batch
- ✓ User-friendly production-floor handling
- ✓ Lower consumption than comparable products
- ✓ Suitable for a broad range of roller applications

FEATURES

- Medium viscosity for even roller spreading
- Compatible with all roller-type melamine machines
- Fast drying on high-speed production lines
- Elastic yet hard film structure
- Reliable performance on varied melamine surfaces
- Minimal carbonisation in the melting tank

SPECIFICATIONS

Viscosity (190°C)	16000 ± 5.000 mPa·s
Softening Point	85 ± 5 °C
Working Temperature	170 ± 10 °C
Colour	Ivory
Shelf Life (Month)	24
Packaging	25 kg Kraft Paper Bag, 25 kg Plastic Drum

Datasheet Disclaimer

The technical values presented in this document are based on laboratory tests and practical application experience. They are provided for general guidance only and should not be considered as product specifications or a guarantee of performance under all operating conditions.

Application performance may vary depending on substrate type, surface preparation, environmental conditions, processing parameters and production methods. Users are responsible for determining the suitability of the product through their own testing before use in commercial production.

As products are continuously improved, technical data may be updated without prior notice. Please contact our technical team for the latest product information and application recommendations.

